



# Meyors Chemical INC Limited

Operational Office Address: Suite 2610-2611 Foreign Trade Building, 239 Zhongxing Road, Luohu District, Shen Zhen City, P R of China Tel: +86-755-8218 4166 Fax: +86-755- 8218 7033 Email: <u>info@meyor.cn</u> URL: <u>www.rbb.com.cn</u>

# DATA-SHEET

| SPECIFICATION & DATA SHEET |                                 | Chemical Analysis: |                         |
|----------------------------|---------------------------------|--------------------|-------------------------|
| Product Code:              | MSHQD -VA033-00 PT              | Chemical Name:     | 4,4' dithiodimorpholine |
| Trade Name:                | Rubber Valcanization Agent DTDM | CAS No.            | 103-34-4                |
| Molecular Formula:         | C8H16N2O2S2                     | Molecular Weight:  | 236.37                  |

Product Information: \*\*\***Specification** 

| Appearance (visual inspection): | White powder | Assay Content % Min            | 94.0  |
|---------------------------------|--------------|--------------------------------|-------|
| Initial M.P.℃ Min:              | 119.0        | Loss on drying (%) $\leqslant$ | 0.5   |
| Ash content (%)≤                | 0.3          | Density at 25℃ (g/cm³)         | 1.360 |
| Residue on (150µm)% sieve≲      | 0.10         |                                |       |

### \*\*\*Typical Properties

White acicular crystal powder. The density is 1.32-1.38 g/cm<sup>3</sup>. Soluble in benzene, CCl<sub>4</sub>, partly soluble in acetone, gasoline, insoluble in alcohol, diethyl ether, water. Decomposing meeting acid or alkali. Stabilization sorage in room temperature. No poison but with high irritating smell. Sensitive to skin and poetasters.

## \*\*\*Recommended Applications

Sulfur donor-vulcanizing agent for efficient vulcanization and semi efficient vulcanization cure system. Provide heat/reversion/aging resistance in NR and Synthetic rubber, Non-blooming. Excellent storage safety. Lower cure rates used alone. Light cure speed when used other sort of accelerators.

#### \*\*\*Handling and Storage recommendations

The product should be stored in the dry and cooling place with good ventilation and should be avoiding hot and sunshine.

6 months with the common storing condition. Recommend use of date is within 3 months.

#### \*\*\*Package

| Bag: 25kg/bag | Pallet(1.1*1.1): 600kg/P |  |
|---------------|--------------------------|--|
|               |                          |  |