



### DATA-SHEET

SPECIFICATION & DATA SHEET		Chemical Analysis:	
Manufacture:	Meyors Chemical INC Limited	Chemical Name:	C <sub>9</sub> petroleum resin
CAS No.:	68477-54-3	Molecular Weight:	Min 600 Max 3000
Trade Name:	C <sub>9</sub> petroleum resin		

#### Product Information:

##### \*\*\*Specification

Product Grade	C9 80-90	C9 90-100	C9 110-120
Product Code:	SP134-02 GT	SP134-00 GT	SP134-03 GT
Appearance (visual):	Yellow granule	Buff or dark amber granule	Yellow granule
Softening Point °C	80-90	90-100	110-120
Ash content (%)≤:	0.05	0.10	0.05
Loss on drying%≤	0.50	0.50	0.50
Acid number (mgKOH/g)	0.3	0.5-1	0.3
Bromine value (g/100g)	20	30~120	30
COLOUR GARDNER (RESIN: TOLUEND=1 : 1)	10MAX	7 MAX	10MAX

##### \*\*\*Typical Properties

The relative density 1.06~1.09(25°C),insolubility in water, methanol, ethanol, solubility in aromatic hydrocarbon and mineral oil.Due to the larger polarity, natural rubber compatibility with the poor, only use in SBR, SIS, SBS, and EVA, PE, PP.

##### \*\*\*Recommended Applications

Improved processing performance synthetic rubber, help with agents scattered powder, Lower temperature mixed iron-smelting and glue viscosity, increase plasticity. Use for PVC, cellulose resins, phenolic resin of modified.

##### \*\*\*Handling and Storage recommendations

# Meyors - RBB



## Meyors Chemical INC Limited

Operational Office Address: Suite 2610-2611 Foreign Trade Building, 239 Zhongxing Road,  
Luohu District, Shen Zhen City, P R of China

Tel: +86-755-8218 4166 Fax: +86-755- 8218 7033

Email: [info@mevor.cn](mailto:info@mevor.cn) URL: [www.rbb.com.cn](http://www.rbb.com.cn)

The product should be stored in the dry and cooling place with good ventilation and should avoid hot and sunshine.

### **\*\*\*Package**

Bag : 25kg/bag

Pallet: 500/1000kg