



# Meyors Chemical INC Limited

Operational Office Address: Suite 2610-2611 Foreign Trade Building, 239 Zhongxing Road, Luohu District, Shen Zhen City, P R of China

> Tel: +86-755-8218 4166 Fax: +86-755- 8218 7033 Email: <u>info@meyor.cn</u> URL: <u>www.rbb.com.cn</u>

# **DATA-SHEET**

SPECIFICATION & DATA SHEET		Chemical Analysis:	
Product Code:	MSHQD -AA034-02PT	Chemical Name:	N-(cyclohexylthio)phthalimide
Trade Name:	Rubber Antiscorching Agent PVI (CTP)	CAS No.:	17796-82-6
Molecular Formula:	C <sub>14</sub> H <sub>15</sub> O <sub>2</sub> SN	Molecular Weight:	261.34
Revision number	02	Date	01/12/2009

### **Product Information:**

# \*\*\*Specification

Appearance (visual inspection):	White powder	Assay content %	95
Initial M.P. Min :	89.0	Loss on drying % :	0.40
Toluene Insoluble%	1.0	Compacted bulk density (kg/m³):	700
Ash content%	0.20	Density at 25 (g/cm <sup>3</sup> )	1.330
Residue on (150µm)% :	0.10	Extra-matter%	0.05

# \*\*\*Typical Properties

White powder. The specific density is 1.25-1.35. Soluble in acetone, benzene, toluol, ethyl acetate, hot CCl<sub>4</sub> and hot alcohol, slightly soluble in gasoline, insoluble in kerosene and water.

### \*\*\*Recommended Applications

PVI can prevent early vulcanizing in glue processing, Improving safety. At the same time significantly improve the storage stability of the glue, preventing natural vulcanization phenomena. In NS, M, DM, CBS, semi-effective orefficient systems, to improve the plastic materials capability. No foam, pollution and other adverse effects. Mainly use for natural and synthetic rubber, particularly with sulfenamide accelerators composing a good sulfuration system

## \*\*\*Handling and Storage recommendations

The product should be stored in the dry and cooling place with good ventilation and should be avoided hot and sunshine.

24 months with the common storing condition. Recommend use of date is within 12 months.

### \*\*\*Package

Bag : 25kg/bag	Pallet(1.1*1.1): 600kg/P
----------------	--------------------------