



# Meyors Chemical INC Limited

Operational Office Address: Suite 2610-2611 Foreign Trade Building, 239 Zhongxing Road, Luohu District, Shen Zhen City, P R of China Tel: +86-755-8218 4166 Fax: +86-755- 8218 7033 Email: <u>info@meyor.cn</u> URL: <u>www.rbb.com.cn</u>

## DATA-SHEET

SPECIFICATION & DATA SHEET		Chemical Analysis:	
Product Code:	MSHQD-AC016-00 GT	Chemical Name:	Zinc diethyl dithiocarbamate
Trade Name:	Rubber Accelerator ZDEC (EZ)	CAS No.:	14324-55-1
Molecular Formula	$C_{10}H_{20}N_2S_4Zn$	Molecular Weight:	361.9
Revision number	02	Date	01/12/2009

Product Information: \*\*\***Specification** 

Appearance (visual inspection):	white granule	Initial M.P. Min:	172			
Zinc content %	17.5-19.5	Loss on drying % :	0.50			
Strength of grain(N)	0.8-2.5	Compacted bulk density (kg/m <sup>3</sup> )	395-435			
Density at 20 (g/cm <sup>3</sup> )	1.480	Accumulate density (kg/m <sup>3</sup> ):	330-370			
Soluble Zinc content%	0.01					
***Trained Drenewice \						

### \*\*\*Typical Properties \

White granule. The specific density is 1.41. Soluble in 1% NaOH solution, CS<sub>2</sub>, benzene, chloroform, slightly soluble in alcohol, insoluble in gasoline.

#### \*\*\*Recommended Applications\

ZDEC is a very fast primary or secondary accelerator for natural and synthetie rubber.it is also a very rapid accelerator for NR and SBR latices.it is a secondary ultra Accelerator for general purpose polymers (NR, SBR, IIR and EPDM), it can be used as primary accelerator in someContinuous cure applications as well as in latex.

### \*\*\*Handling and Storage recommendations

The product should be stored in the dry and cooling place with good ventilation and should be avoiding hot and sunshine.

Usually the shelf time is 12 months while the recommend use of date is 6 months.

#### \*\*\*Package\

Bag: 25kg/bag	Pallet(1.1*1.1): 600kg/P	