



Meyors Chemical INC Limited

Operational Office Address: Suite 2610-2611 Foreign Trade Building, 239 Zhongxing Road, Luohu District, Shen Zhen City, P R of China Tel: +86-755-8218 4166 Fax: +86-755- 8218 7033 Email: <u>info@meyor.cn</u> URL: <u>www.rbb.com.cn</u>

DATA-SHEET

SPECIFICATION & DATA SHEET		Chemical Analysis:	
Product Code:	MSHQD-AC016-00 OT	Chemical Name:	Zinc diethyl dithiocarbamate
Trade Name:	Rubber AcceleratorZDEC (EZ)	CAS No.:	14324-55-1
Molecular Formula	$C_{10}H_{20}N_2S_4Zn$	Molecular Weight:	361.9
Revision number	02	Date	01/12/2009

Product Information: *****Specification**

Appearance (visual inspection):	white powder	Initial M.P. Min:	172		
Zinc content %	17.5-19.5	Loss on drying % :	0.50		
Residues(150µm)% :	0.10	Compacted bulk density (kg/m ³):	395-435		
Residues(63µm)% :	0.50	Accumulate density (kg/m ³):	330-370		
Oil Content%	1.0-2.0	Density at 20 (g/cm ³)	1.480		
Soluble Zinc content%	0.01				

***Typical Properties

White powder. The specific density is 1.41. Soluble in 1% NaoH solution, CS₂, benzene, chloroform, slightly soluble in alcohol, insoluble in gasoline.

***Recommended Applications

ZDEC is a very fast primary or secondary accelerator for natural and synthetie rubber.it is also a very rapid accelerator for NR and SBR latices.it is a secondary ultra

Accelerator for general purpose polymers (NR, SBR, IIR and EPDM), it can be used as primary accelerator in some Continuous cure applications as well as in latex.

***Handling and Storage recommendations

The product should be stored in the dry and cooling place with good ventilation and should be avoiding hot and sunshine.

Usually the shelf time is 12 months while the recommend use of date is 6 months.

***Package

Bag: 25kg/bag

Pallet(1.1*1.1): 600kg/P