



DATA-SHEET

SPECIFICATION & DATA SHEET		Chemical Analysis:	
Product Code:	MSHQD-AC003-00 OT	Chemical Name:	Zinc 2-mercaptobenzothiazole
Trade Name:	Rubber Accelerator ZMBT (MZ)	CAS No.	155-04-4
Molecular Formula	C14H8N2S4Zn	Molecular Weight:	397.86
Revision number	02	Date	01/12/2009

Product Information:

*****Specification**

Appearance (visual inspection):	Light yellow powder	Loss on drying % :	0.50
Initial M.P. :	200.0	Zinc Content %:	16.0-22.0
Residues(150um)% :	0.10	Bulk density (kg/m3):	470-510
Free MBT % :	5.0	Oil Content %	1.0-2.0
Compacted bulk density (kg/m ³)	480-520		

*****Typical Properties**

Light yellow powder with light bitter taste. The specific density is 1.65--1.72. Hardly soluble in acetone, benzene, ethanol, and carbon tetrachloride. Insoluble in water, gasoline. It will be decomposed with strong acid and alkali.

*****Recommended Applications**

In latex vulcanization ZMBT is used in combination with ZBEC, ZDMC and ZDEC. ZMBT does not destabilize latex formulations.
 In latex thread applications the low free MBT grade of ZMBT provide reduced extraction of MBT during acid coagulation (acid bath pollution) and helps to stabilize the viscosity of latex compounds during storage.
 In dry rubber applications the performance of ZMBT is almost similar to MBT, but with a slight scorch improvement.

****Handling and Storage recommendations**

Store ZMBT in a cool, dry, well ventilated area, avoiding exposure of the packaged products to direct sunlight. Usually the shelf time is 24 months while the recommend use of date is in 12 months.

*****Package**

Bag : 25kg/bag	Pallet(1.1*1.1) : 600kg/P
----------------	---------------------------